

Features & Benefits

- Prevents vibration loosening
- Controlled off-torque
- Non-drip, thixotropic
- Full cure at room temperature
- Provides corrosion protection
- Superior environmental resistance
- Environmentally friendly – 100% solids

Description

Permabond® HH120 Threadlocker is an excellent general purpose threadlocker and sealant. It is used for locking bolts, nuts and screws that require permanent assembly. Its high viscosity allows for ease of use on coarse threaded fasteners. Cure is fast and reliable on steel, cadmium, zinc and other plated fasteners. Major use areas include machinery and equipment manufacturing. Additional uses include sealing pipe flanges and retaining worn bearings.

MIL-S-46163A & MIL-S-22473E

Permabond® HH120 is tested to the lot requirements of Mil-S-46163A and Mil-S-22473E.

ASTM D5363

Permabond® HH120 is tested to the general requirements defined in section 5.1.1 and 5.1.2 and to the detailed requirements defined in section 5.2 of ASTM D5363.


Physical Properties of Uncured Adhesive

Chemical composition	Methacrylate esters
Appearance	Red
Viscosity @ 25°C	7,000 mPa.s (cP)
Specific Gravity	1.1
UV fluorescence	Yes

Typical Curing Properties

Maximum gap fill	0.25 mm 0.01"
Maximum thread size	M30 1½"
Time taken to reach handling strength (M10 steel) @23°C	10 minutes*
Time taken to reach working strength (M10 steel) @23°C	30 minutes
Full strength (M10 steel) @23°C	24 hours

Strength Development



*Cure times are typical at 23°C. Copper and its alloys will follow the faster cure while oxidised or passivated surfaces like stainless steel will tend towards the slower curve. Lower temperatures or large gaps will tend to extend the cure time. To reduce the cure time the use of Permabond A905, ASC10, or heat can be considered.


Typical Performance of Cured Adhesive

Torque strength (M10 steel ISO10964)	Break 31 N·m 275 in.lb Prevail 34 N·m 300 in.lb
Shear strength (steel collar & pin ISO10123)	17 MPa 2500 psi
Coefficient of thermal expansion	90 x 10 ⁻⁶ mm/mm/°C
Dielectric strength	11 kV/mm
Thermal conductivity	0.19 W/(m.K)

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Hot Strength



"Hot strength" Breakaway strength on M10 Zinc plated bolts according to ISO 10964. Cured at 23°C for 24 hours then conditioned for 30 minutes at testing temperature.

HH120 can withstand higher temperatures for brief periods (such as for paint baking and wave soldering processes) providing the joint is not unduly stressed. The minimum temperature the cured adhesive can be exposed to is -55°C (-65°F) depending on the materials being bonded.

Chemical Resistance

Immersion (340 hours)	Temperature, °C (°F)	Strength Retention (%)
Water	75 (168)	100
Butyl alcohol	75 (168)	100
Toluene	75 (168)	99
Motor oil	75 (168)	99
Hydrocarbon test fluid	75 (168)	100
JP4-Jet fuel	75 (168)	93
JP5-Jet fuel	75 (168)	100
Ethylene glycol	75 (168)	99

This product is not recommended for use in contact with oxygen, oxygen rich systems and other strong oxidizing materials. This product may adversely affect some thermoplastics and users must check compatibility of the product with such substrates before using.

Surface Preparation

Though the anaerobic adhesives will tolerate a slight degree of surface contamination, best results are obtained on clean, dry and grease free surfaces. The use of a suitable solvent-based cleaner (such as acetone or isopropanol) is recommended.

In general, roughened surfaces (~25µm) give higher bond strengths than polished or ground surfaces.

To reduce the curing time, especially on inactive surfaces (such as zinc, aluminium and stainless steel), the use of Permabond A905 or ASC10 can be considered.

Directions for Use

- 1) Prevent the tip from touching metal surfaces during application.
- 2) When working with through holes, dispense a bead of material across the contact length of the threads.
- 3) When working with blind holes, apply several drops down the threads to the bottom of the hole.
- 4) Assemble and torque the parts as necessary.
- 5) Replace lid to bottle to avoid contamination of remaining liquid adhesive.

Video Link

Threadlocker directions for use:

<https://youtu.be/-Ueg0QO10pQ>



Storage & Handling

Storage Temperature

5 to 25°C (41 to 77°F)

Users are reminded that all materials, whether innocuous or not, should be handled in accordance with the principles of good industrial hygiene. Full information can be obtained from the Safety Data Sheet.

This Technical Datasheet (TDS) offers guideline information and does not constitute a specification.

www.permabond.com

• UK: 0800 975 9800

• General Enquiries: +44 (0)1962 711661

• US: 732-868-1372

• Asia: + 86 21 5773 4913

info.europe@permabond.com

info.americas@permabond.com

info.asia@permabond.com

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. In every case we urge and recommend that purchasers before using any product in full-scale production make their own tests to determine to their own satisfaction whether the product is of acceptable quality and is suitable for their particular purpose under their own operating conditions. THE PRODUCTS DISCLOSED HEREIN ARE SOLD WITHOUT ANY WARRANTY AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED.

No representative of ours has any authority to waive or change the foregoing provisions but, subject to such provisions, our engineers are available to assist purchasers in adapting our products to their needs and to the circumstances prevailing in their business. Nothing contained herein shall be construed to imply the non-existence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of this patent. We also expect purchasers to use our products in accordance with the guiding principles of the Chemical Manufacturers Association's Responsible Care® program.

Permabond HH120

Global TDS Revision 4

17 October 2016

Page 2/2

FOR PROFESSIONAL OR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN